



# Bona Domo™

## One-Component Waterborne Wood Floor Finish

Easy-to-use quick drying formula.



Bona Domo™ is easy and forgiving to apply with a roller or T-bar. This one-component, non-yellowing formulation comprises all essential properties for finishing and protecting wood floors. And because it's waterborne with low VOCs, Bona Domo provides a healthy environment.

- Apply with Roller or T-bar
- Forgiving/Easy Application
- Easy to Abrade
- Non-Yellowing Formula
- Low Odor
- GREENGUARD Certified
- Available in both Satin-Matte and Semi-Gloss



# Bona Domo™

One-Component Waterborne Wood Floor Finish

**Easy-to-use quick drying formula.**

## PHYSICAL CHARACTERISTICS

- Color** – Milky white (wet)
- pH** – 7.6-8.0
- Solids** – 28%
- Density** – 8.7 lbs/gallon 1.04 (g/ml)
- US Regulatory VOC** – 275 g/L
- Gloss Level** – Satin-Matte 15-20, Semi-Gloss 40-45
- Odor** – Non-offending
- Stability** – 1-year shelf life in unopened container
- Packaging** – 1-gallon plastic bottle

## APPLICATION CHARACTERISTICS

- Clarity** – Clear and colorless when dry
- Leveling** – Excellent
- Defoaming** - Excellent
- Drying Time** – 2-3 hours
- Coverage** – 500-600 square feet per gallon
- Percent Cured After 24 Hours** – 70%
- Maximum Cure** – 100% after 1 week

## RECOMMENDED USE

Residential - kitchens, entryways, family rooms, homes with pets, and/or children, and anywhere an oil-based finish would be used.

## DIRECTIONS

BEFORE USING, READ ALL DIRECTIONS AND SAFETY DATA SHEETS.

FOR TECHNICAL ADVICE: Call Bona US at 800-872-5515

## COMPATIBILITY

Bona Domo will adhere to most stains and finishes after proper preparation and dry times. Stain, sealer, and finish results may vary widely depending on the wood species, especially on oily and resinous exotic species. ALWAYS PREPARE A SAMPLE OR TEST

AREA TO DETERMINE COMPATIBILITY, APPEARANCE AND DESIRED RESULTS.

## SANDING AND PREPARATION OF NEW FLOORS

1. Sand and prepare floor using accepted industry association methods. 2. For a stained floor, make your final cut with 80 to 100-grit paper, then multidisc with 80 to 120-grit paper. For an unstained floor, make your final cut with 80 to 120-grit paper, then multidisc with 120 to 150-grit paper. This burnishing will reduce the amount of grain raise. 3. Use a Tampico Brush on a buffer and vacuum thoroughly. 4. Tack with a dry Bona® Microfiber Cleaning Pad or cloth. 5. Apply Bona Finishing system.

## The Bona Domo™ FINISH SYSTEM

Apply sealer or Bona stain and two coats of Bona Domo. Follow label directions. Adding a third coat of Bona Domo is recommended in heavy-traffic commercial and residential areas. Visit [bona.com](http://bona.com) for additional product and application information.

## RECOMMENDED APPLICATORS:

Bona® Floor Coater, Bona® Roller, Bona® Cut-In pad

## MIXING INSTRUCTIONS

SHAKE WELL BEFORE USING. DO NOT THIN.

## FINISHING

1. Pour a 6"- wide line of finish along the starting wall. Go with the grain of the wood. 2. Using a pre-dampened Bona floor coater, draw the floor coater forward with the grain of the wood, moving the finish toward the opposite wall. To maintain a wet edge at all times, hold the floor coater at a snowplow angle. 3. At the end of each run, turn the floor coater and pull it toward you through the puddle; then pad out the floor coater parallel to the wet edge. 4. Feather out all turns. Do not push too hard or too fast to avoid drips flying off



# Bona Domo™

## One-Component Waterborne Wood Floor Finish

### Easy-to-use quick drying formula.

the floor coater. 5. BE SURE YOU ARE USING THE RECOMMENDED COVERAGE OF 500-600 SQ. FT. PER GALLON. DO NOT SPREAD TOO THIN. 6. Allow the first coat to dry 2-3 hours. High humidity and/or low temperature conditions will extend the dry time (recommended conditions of 65-80°F/40-60% relative humidity). 7. For smoothest results, see INTERCOAT ABRASION. At a minimum between coats, vacuum and tack thoroughly with a Bona Microfiber Cleaning Pad (dry or slightly dampened with water).

### INTERCOAT ABRASIONS

It is not necessary to abrade between Bona waterborne sealer and finish coats unless more than 48 hours has passed since the previous coat was applied. For smoothest results, abrade between each coat as necessary, using a multidisc and Bona Diamond 180 to 240-grit abrasives with Bona Intermediate Pads. Thoroughly clean abraded floor using Bona PowerScrubber® OR vacuum and tack with Bona Microfiber Cleaning Pads (dry or slightly dampened with water). When using solvent-based sealers, ALWAYS abrade, vacuum and tack before finish coats.

### RECOATING

Be sure floor is free from wax, polish, and oily residues. If contaminants are present, use the full Bona Recoat System™ to ensure adhesion. Otherwise, follow the Bona Prep® process. Adhesion failure can occur if these recoating processes are not followed and the floor has not been tested for compatibility.

### CURING

The curing process takes approximately 7 days, (70% cured after 1 day, 100% after 7 days). The floor may be walked on after 24 hours but remains susceptible to scuffing or marring until completely cured. Furniture can be moved back in carefully after 3 days. Do not replace area rugs until the floor has fully cured.

### CLEAN-UP

Application tools should be thoroughly cleaned with water and stored in an airtight container. Dispose of any remaining product in accordance with local, state, and federal regulations.

### FLOOR CARE

Use only a dry Bona Microfiber Mop or cloth for cleaning during the first week. Put walk-off mats at all entrance doorways to keep out excessive dirt and grit. Sweep or vacuum daily and clean as needed with Bona® Hardwood Floor Cleaner. Use felt pads under furniture legs and appliances.

### STORAGE

Nonflammable – Bona Domo should be stored in a climate-controlled environment. KEEP FROM FREEZING. Do not store above 100° F.



# Bona Domo™

One-Component Waterborne Wood Floor Finish

Easy-to-use quick drying formula.

## ORDERING INFORMATION

Item #	Description	Sheen	Sheen Level	Size	No/Case	Weight (lbs.)
WT220318001	Bona Domo	Semi-Gloss	40-45	Gallon	3	28.74
WT220618001	Bona Domo	Satin-Matte	15-20	Gallon	3	28.74
WT220355001	Bona Domo	Semi-Gloss	40-45	5-gallon	1	45
WT220655001	Bona Domo	Satin-Matte	15-20	5-gallon	1	45